

Aluminium Powder

Light weight concrete

Product Code	Particle Size Wet Sieve (ISO - 1247) <45 µm(%)	Metallic aluminium (Gas Volumetry) (% typical)	Particle size distribution D (50%) (CILAS- 1064) (µm approx.)	Apparent Density (Loose Pouring house method) (g/cc)	Surface area (cm ² /g min)
O4C	88 min	90	20+/-5	0.14 – 0.20	15000
O3C	80 min	90	30+/-5	0.13 – 0.20	10000
O2C	65 – 80	90	40+/-5	0.13 – 0.20	9000
O1C	45 – 65	91	45+/-5	0.13 – 0.20	8000

